



Europäisches Patentamt
European Patent Office
Office européen des brevets

⑪ Publication number:

0 112 406
A1

⑫

EUROPEAN PATENT APPLICATION

⑮ Application number: 82112009.4

⑤① Int. Cl.²: B 32 B 27/08

⑯ Date of filing: 24.12.82

⑬ Date of publication of application: 04.07.84
Bulletin 84/27

⑦① Applicant: Toppan Printing Co., Ltd., 5-1, 1-chome, Taiko, Taiko-ku Tokyo (JP)

⑦② Inventor: Iwasawa, Nobuyuki, 5-9-20, Hiyoshi Kohoku-ku, Yokohama-shi Kanagawa-ken (JP)
Inventor: Kazato, Keiji, 60-1, Isobe, Chiba-shi Chiba-ken (JP)

⑰ Designated Contracting States: DE FR GB

⑦④ Representative: Bühling, Gerhard, Dipl.-Chem. et al, Patentanwaltsbüro Tiedtke-Bühling-Kinne-Gruppe-Pellmann-Grams Bavariaring 4, D-8000 München 2 (DE)

⑤④ Multi-layered hollow container.

⑤⑦ A multi-layered hollow container comprises an inner layer made of a thermoplastic fluorocarbon resin, an intermediate layer made of a mixed resin comprising 80 to 30% by weight of a polyolefin grafted with an unsaturated glycidyl compound and 50 to 10% by weight of a polyolefin, and an outer layer made of a polyolefin. This container is capable of being formed in an economical and cheap manner by the multi-layer co-extrusion blow molding method and has a good chemical resistance to agricultural chemicals, fuel oil and industrial chemicals and a good interlaminar strength and water-vaporproof property.

EP 0 112 406 A1

Background of the Invention

1. Field of the Invention

The present invention relates to a container
suitable for containing agricultural chemicals, fuel
oil and industrial chemicals.

2. Description of the Prior Art

Heretofore, containers made of polyolefins such as
polyethylene or polypropylene have been generally used
for holding agricultural chemicals, fuel oil and
industrial chemicals such as those of aromatic hydro-
carbon series or aliphatic hydrocarbon series. These
containers, however, are unsatisfactory because they
swell or crack after a certain period of time in view
of a poor resistance to chemicals so that they cannot
be widely used from the viewpoint of safety.

In order to improve the chemical resistance, the
use of a resin having good resistance to organic
chemicals such as nylon has been proposed. Although an
attempt has long been made to produce hollow containers
made singly of nylon, those containers have not yet
been commercialized because of their various disadvan-
tages and difficulties such as a high cost of nylon, a
poor moldability and drawdown owing to the low molten
viscosity, and a low fused adhesion strength of the
pinch-off portion in the bottom of nylon single layer
container leading to an easy separation of the
pinch-off portion if the container is dropped.

Therefore, contents such as agricultural chemicals, fuel oil and industrial chemicals have been generally held in metallic cans or glass bottles at the present time. However, disposal of wastes of metallic
5 cans and glass bottles after use thereof has become a social problem. In place of these containers, containers suitable for filling such contents have long been desired.

As the method of coping with those prior art
10 problems, for example, as shown in Japanese Patent Laid-Open Publication No. 53-21675 (1978), the production of a three-layer container having an excellent chemical resistance and moldability by the multi-layer co-extrusion blow molding method has now
15 been developed and put to practical use. This three-layer container comprises an intermediate layer consisting of an adhesive polyolefin, and an inner layer, which is brought into direct contact with liquid contents, consisting of nylon or saponified ethylene-vinyl acetate copolymer having an excellent resistance
20 particularly to organic solvents and so on. These resins, however, do not exhibit an excellent resistance to all liquid contents. For example, nylon is very poor in resistance to phenols, alcohols, strong acids
25 and weak acids. The saponified ethylene-vinyl acetate copolymers have the defect that they do not have a sufficient resistance to solvents having a hydroxyl

group as in the case of nylon. Metals are inappropriate for acids, and glass is inappropriate for alkaline hydrates.

5 A fluorocarbon resin is generally known as a material exhibiting an excellent resistance to all chemicals. The fluorocarbon resin is generally excellent in chemical resistance and has no water absorption properties, and its abrasion resistance, self lubrication and non-tackiness are the best among
10 synthetic resins. Tetrafluoroethylene resin (hereinafter referred to as TFE) is known most among the fluorocarbon resins. TFE has the lowest chemical activity possible as a fluorine-containing polymer, lowest friction, non-tackiness, best dielectric
15 performance, minimum water absorption, highest resistance to high and low temperatures and best weathering property among the fluorocarbon resins. However, TFE does not have a plasticity so as to be molten at its melting point so that its processability
20 is extremely poor. Accordingly, it is processed according to a method similar to that adopted in the field of powder metallurgy so that its use is limited.

25 A thermoplastic fluorocarbon resin which is extrusion moldable may include ethylene-tetrafluoroethylene alternating copolymer resin (hereinafter referred to as ETFE), polyvinylidene fluoride resin (PVDF), polyvinyl fluoride resin (PVF),

ethylene-ethylene chloride trifluoride alternating
copolymer resin (ECTFE), polyethylene chloride
trifluoride resin (PCTFE) and
5 tetrafluoroethylene-hexafluoroethylene alternating
copolymer resin (FEP). These resins contain fluorine
atoms in their molecular segments so that they exhibit
properties similar to those of TFE. Although the
fluorocarbon resins have favorable properties, they are
very expensive so that their use is restricted to some
10 special fields from economical aspects.

The thermoplastic fluorocarbon resins also have
difficulty in laminating with other resins because they
generally have significant non-tackiness.

As the method of overcoming those defects as set
15 forth hereinabove, we have disclosed in our copending
Japanese Patent Laid-Open Publication No. 56-13337
(1981) the multi-layer co-extrusion blow molding method
adapted to produce a container having a favorable
chemical resistance, water-vaporproof, interlaminar
20 strength and economy in production, the container
comprising an inner layer made of a thermoplastic
fluorocarbon resin, an intermediate layer made of a
polyolefin grafted with an unsaturated glycidyl
compound, and an outer layer made of a polyolefin.
25 This method, however, has the defect that it has a poor
co-extrusion blow moldability although the interlaminar
strength is satisfactory. In this method, the

fluorocarbon resin to be used as the inner layer has a high molding temperature ranging from 250 to 350°C, so that the molten viscosity of the unsaturated glycidyl graft-modified polyolefin as the intermediate layer to be extruded as a laminate with the fluorocarbon resin decreases remarkably leading to irregularities in wall thickness in the inner and intermediate layers in the circumferential direction of the resulting container. In some extreme cases, the graft-modified polyolefin for the intermediate layer cannot be filled to form a full intermediate layer resulting in a container wherein the thermoplastic fluorocarbon resin and the polyolefin are locally separate from each other.

Summary of the Invention

The present invention has been made in consideration of the above drawbacks and has for its object to provide a multi-layered hollow container capable of being formed in an economical and cheap manner by the multi-layer co-extrusion blow molding method using the thermoplastic fluorocarbon resin having a good co-extrusion blow moldability, chemical resistance, water-vaporproof and interlaminar strength.

Detailed Description of the Preferred Embodiments

The multi-layered hollow container according to the present invention consists mainly of an inner layer made of a thermoplastic fluorocarbon resin, an intermediate layer made of a mixed resin of 80 to 30% by

weight of a polyolefin grafted with an unsaturated glycidyl compound, 35 to 5% by weight of a gum rubber and 50 to 10% by weight of a polyolefin; and an outer layer made of a polyolefin.

5 The intermediate layer may preferably be made of a mixed resin of 65 to 50% by weight of ethylene-vinyl acetate copolymer graft-modified with an unsaturated glycidyl compound, 25 to 15% by weight of a gum rubber and 30 to 20% by weight of a polyolefin.

10 The fluorocarbon resin to be used for the inner layer of the multi-layered hollow container according to the present invention may include, for example, ETFE, PVDF, PVF, ECTFE, PCTFE and FEP. Among these fluorocarbon resins, ETFE, PVDF and FEP are preferred
15 from a viewpoint of molding processability. Further, ETFE is most suitable for accomplishing the objects of the present invention because it has a high resistance to solvents.

20 In accordance with the present invention, the polyolefin to be used as the outer layer of the container may include, for example, high, medium and low density polyethylene, polypropylene and ethylene-propylene copolymer.


25 When the polyolefin is mixed with an inorganic filler and a fiber, a thermal resistance, flammability and mechanical strength are improved.

The amount of the inorganic filler or fiber to be used in accordance with the present invention may range from 5 to 90% by weight with respect to 10 to 95% by weight of the polyolefin, preferably from 20 to 60% by weight with respect to 40 to 80% by weight of the polyolefin. The inorganic filler may include, for example, calcium carbonate, aluminum hydroxide, calcium sulfite, talc, gypsum and mica. The fiber may include, for example, an inorganic fiber, an organic fiber and carbon fiber. Among these fibers, glass fibers which are preferred in terms of cost and properties. The average lengths of the glass fibers are in the range from 0.05 to 30 mm, preferably from 0.2 to 15 mm.


The polyolefin graft-modified with the unsaturated glycidyl compound to be used for the intermediate layer according to the present invention may firmly adhere the fluorocarbon resin and the polyolefin together as illustrated hereinabove.

The unsaturated glycidyl compounds may include, for example, glycidyl methacrylate and glycidyl acrylate. These compounds have the following chemical structures:

glycidyl methacrylate:



glycidyl acrylate:



The modified polyolefin may be a graft polymer prepared, for example, by mixing polyethylene, polypropylene or a copolymer thereof or an ethylene-vinyl acetate copolymer with the unsaturated glycidyl compound as described hereinabove and then subjecting the resulting mixture to radioactive radiation or a reaction in the presence of a peroxide catalyst. The graft-polymerizable polyolefin may include, for example, polyethylene, polypropylene or a copolymer thereof or an ethylene-vinyl acetate copolymer as illustrated hereinabove. Among these polyolefins, an ethylene-vinyl acetate copolymer is preferred in terms of graft polymerization.

The gum rubber has the great effect of improving the molten viscosity of the unsaturated glycidyl graft-modified polyolefin, particularly the unsaturated glycidyl graft-modified ethylene-vinyl acetate copolymer, and may not decrease the interlaminar strength between the thermoplastic fluorocarbon resin and the polyolefin. The addition of the gum rubber, however, may cause melt fractures of a multi-layered molten parison leading to irregularities in the wall thicknesses of the intermediate layer and the inner layer. In order to improve this property, the polyolefin as

illustrated hereinafter is added. With increasing amounts of the polyolefin, moldability and uniformity in wall thickness of the intermediate layer and the inner layer may be improved; however, interlaminar strength decreases to a remarkable extent.

Accordingly, the amounts of the gum rubber are preferably within the range as defined hereinabove.

The gum rubber may include, for example, natural rubber, styrene-butadiene rubber, acrylonitrile-butadiene rubber, butyl rubber, chloroprene type synthetic rubber, acryl rubber, urethane rubber, polybutadiene rubber, ethylene-propylene rubber, ethylene-propylene terpolymer, polyether rubber, polybutene-1 rubber and ethylene-butadiene rubber. Among these gum rubbers, ethylene-propylene rubber and ethylene-propylene terpolymer are desirable in terms of compatibility with the unsaturated glycidyl graft-modified ethylene-vinyl acetate copolymer or the polyolefin, moldability and cost.

The polyolefin to be used for the intermediate layer of the container according to the present invention may include, for example, α -olefin homopolymer such as polyethylene or polypropylene, a copolymer of ethylene with other α -olefin such as an ethylene-propylene copolymer, ethylene-butene-1 copolymer or ethylene-hexane-1 copolymer or a crystalline polymer of α -olefins such as propylene-butene-1. These

polymers and copolymers may be blended with each other. A high density polyethylene having a low melt index may be preferably used in terms of compatibility with the gum rubber and the unsaturated glycidyl graft-modified ethylene-vinyl acetate copolymer, the effect of decreasing a molten viscosity, and cost.

The three-layer hollow container according to the present invention may be molded by conventional multi-layer extrusion blow molding method. It is economical to prepare the container so that it has a thin inner layer made of the fluorocarbon resin and a thick outer layer made of general-purpose polyolefin.

With the hollow container formed as having the structure as described hereinabove, the present invention can provide the multi-layered hollow container having an excellent chemical resistance obtainable at a cheaper cost than conventional ones and without causing the fluorocarbon resin to lose its properties as well as having excellent co-extrusion blow moldability and interlaminar strength due to the use of the resin mixture of the unsaturated glycidyl graft-modified polyolefin with the gum rubber and the polyolefin as the intermediate layer between the inner layer made of the fluorocarbon resin and the outer layer made of the polyolefin. With high density polyethylene, a container suitable for containing chemicals having an excellent impact resistance may be

provided. The use of polypropylene may provide a container for containing medicines and drugs which may be sterilizable by heat.

Example 1

5 Using high density polyethylene (HDPE) having a density of 0.95 and a melt index of 0.3 as the outer layer, a resin mixture of 45% by weight of graft polymer obtained by grafting an ethylene-vinyl acetate copolymer having a density of 0.94 and a melt index of 1.8 with glycidyl methacrylate with 20% by weight of ethylene-propylene terpolymer (ethylene content: 70%; propylene content: 15%; and ethylidenenorbornene content: 15%) and 35% by weight of high density polyethylene having a density of 0.955 and a melt index of 0.05 as the intermediate layer, and ethylene-tetra-fluoroethylene alternating copolymer resin (ETFE) having a melting point of 270°C and a molten viscosity ranging from 10^4 to 10^5 at temperatures ranging from 300 to 330°C as an inner layer, a three-layer hollow container having a weight of 45 grams and an inner content of 500 cc was prepared by the multi-layer co-extrusion blow molding machine. The outer layer/intermediate layer/inner layer ratio in wall thickness was found to be 7/1/2.

25 Example 2

 A three-layer hollow container was prepared by using the same materials and following the same

procedures as in Example 1 with the exception that a resin mixture of 55% by weight of an ethylene-vinyl acetate copolymer having a density of 0.94 and a melt index of 1.8 grafted with glycidyl methacrylate with
5 25% by weight of an ethylene-propylene terpolymer (ethylene content: 70%; propylene content: 15%; and ethylidenenorbornene content: 15%) and 20% by weight of high density polyethylene having a density of 0.955 and a melt index of 0.05 was used for the intermediate
10 layer.

Example 3

A three-layer hollow container having a weight of 45 grams and an inner content of 500 cc was prepared by using the same materials and following the same
15 procedures as in Example 1 with the exception that a blend of 70% by weight of HDPE of Example 1 with 30% by weight of glass fibers having an average length of 10 mm was used for the outer layer. The outer/intermediate/inner layer ratio in wall thickness was found
20 to be 7/1/2.

Comparative Example 1

A three-layer hollow container was prepared by using the same materials and following the same
25 procedures as in Example 1 with the exception that an ethylene-vinyl acetate copolymer having a density of 0.94 and a melt index of 1.8 grafted with glycidyl methacrylate was used as the intermediate layer. This

three-layer container was found to be remarkably irregular in wall thickness in the inner layer and the intermediate layer, and some portions of the intermediate layer were deficient so that its commercial value was found to be insufficient.

Comparative Example 2

A three-layer hollow container was prepared in the same manner as in Example 1 with the exception that a mixture of 70% by weight of an ethylene-vinyl acetate copolymer having a density of 0.94 and a melt index of 1.8 grafted with glycidyl methacrylate and 30% by weight of an ethylene-propylene terpolymer (ethylene content: 70%; propylene content: 15%; and ethylidene-norbornene content: 15%) was used for the intermediate layer. This three-layer molten parison caused melt fractures and led to irregularities in wall thickness.

The interlaminar or adhesion strength and moldability of the containers are shown in a table below.



0112406

	*1 Adhesion strength (g/15 mm width)	*2 Moldability
Example 1	200 - 300	⊙
Example 2	500 - 700	○
Example 3	200 - 300	⊙
Comparative Example 1	700 - 800	x
Comparative Example 2	700 - 800	x

*1) 90° peeling (interlaminar strength between the inner and intermediate layers)

*2) Moldability: ⊙ Excellent
○ Good
x Remarkably poor

What is claimed is:

1. A multi-layered hollow container comprising an inner layer made of a thermoplastic fluorocarbon resin, an intermediate layer made of a mixed resin comprising
5 80 to 30% by weight of a polyolefin grafted with an unsaturated glycidyl compound and 50 to 10% by weight of a polyolefin, and an outer layer made of a polyolefin.
2. A multi-layered hollow container according to
10 claim 1, wherein the inner layer comprises an ethylene-tetra-fluoroethylene copolymer (ETFE).
3. A multi-layered hollow container according to claim 1 or 2, wherein the polyolefin grafted with the
15 unsaturated glycidyl compound is an ethylene-vinyl acetate copolymer grafted with an unsaturated glycidyl compound.
4. A multi-layered hollow container according to claim 3, wherein the intermediate layer comprises 65 to
20 50% by weight of the ethylene-vinyl acetate copolymer grafted with the unsaturated glycidyl compound, 25 to 15% by weight of a gum rubber, and 30 to 20% by weight of a polyolefin.
5. A multi-layered hollow container according to
25 any one of claims 1 to 4, wherein the gum rubber is ethylene-propylene gum or an ethylene-propylene terpolymer.

6. A multi-layered hollow container according to any one of claims 1 to 5, wherein the outer layer comprises a polyolefin containing an inorganic filler or a fiber.

5

10

15

20

25



European Patent
Office

EUROPEAN SEARCH REPORT

01124061
Application number

EP 82 11 2009

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 7)
D, A	JAPANESE PATENTS GAZETTE, Section Ch: Chemical, Week D14, unexamined: 9th-15th February 1981, J5, page 7, no. 24132 D/14, Derwent Publications Ltd., London, G.B. & JP - A - 56 013 337 (TOPPAN PRINTING K.K.) 09-02-1981	1, 6	B 32 B 27/08
A	--- EP-A-0 016 617 (MITSUI PETROCHEMICAL IND.) * Claims 1,7; page 12, line 34 - page 13, line 27 *	1, 5, 6	
A	--- EP-A-0 012 434 (HOECHST) * Claims 1,2; page 8, line 36 - page 11, line 34 * -----	1, 2	
			TECHNICAL FIELDS SEARCHED (Int. Cl. 7)
			B 32 B B 65 D
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 02-08-1983	Examiner BLASBAND T.
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EPO Form 1503 03/82

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.